



Test Report No. 68.401.23.0236.01C
Rev. 00
Dated 2023-02-24

Applicant: Qingyuan Weichangda Chemical Co., Ltd.
Address: No.1 Xingyuan Road, Minzu Industrial Zone, Lianzhou, Qingyuan City, Guangdong Province
Attn.: Ms. Xie
Sample Description: Non Stick Coating
Model No.: DF1500-XXXX, DF1600-XXXX, DF1800-XXXX, DF7600-XXXX
Sample Received Date: 2023-02-20
Test Period: From 2023-02-20 to 2023-02-24
Location of Testing: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Purpose of examination: As specified by client, to test as regulated by the
- U.S. F.D.A. C.F.R. 21
- Consumer Product Safety Commission of U.S.A. Title 16, Code of Federal Regulation, part 1303
Test Result: Refer to following page(s)
Remark: The result relates only to the items tested.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:

Sean Shen
Project Handler



Reviewed by:

Scarlett Liang
Designated Reviewer

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

Disclaimer Measurement Uncertainty: Unless otherwise agreed upon, pass or fail verdicts are given based on the measured values without consideration of measurement uncertainties. Please note, every test method has a measurement uncertainty which has been evaluated by the laboratory according to ISO IEC 17025 requirements. By taking measurement uncertainties into account it might happen that measured values can neither be assessed as pass or fail.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12 & 13, Zhiheng Wisdomland Business Park,
Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong 518052 China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299



Test Report No. 68.401.23.0236.01C
Rev. 00
Dated 2023-02-24

SUMMARY OF TEST RESULTS


No.	Test Requested	Conclusion	Remarks
1.	For material: Resinous and polymeric coatings - Test for compliance with U.S. F.D.A. C.F.R. 21. Part 175.300	PASS	
2.	For material: Coating - Total Lead Test for compliance with Consumer Product Safety Commission of U.S.A. Title 16, Code of Federal Regulation, part 1303 (CPSC 16 CFR 1303)	PASS	





Test Report No. 68.401.23.0236.01C
Rev. 00
Dated 2023-02-24

1. TESTED SUBJECT DESCRIPTION

Test No.	Sample No.	Tested Material Description	Photo
T1	003	Black Non-stick coating	





2. TEST RESULT

2.1. TEST FOR COMPLIANCE WITH U.S. F.D.A. C.F.R. 21. PART 175.300

Test Item	Result [mg/in ²]	CFR Specification [mg/in ²]
	Sample 003	
Total extractives in distilled water (250°F for 2 hours)	< 1.0	≤ 18
Total extractives in 8% ethanol (250°F for 2 hours)	< 1.0	≤ 18
Total extractives in n-Heptane (150°F for 2 hours)	< 1.0	≤ 18

Note :

- “mg/in²” denotes milligram per square inch
- “°F” denotes degree Fahrenheit
- “<” denotes less than
- “≤” denotes not more than
- The specification is quoted from U.S. F.D.A. C.F.R. 21. Part 175.300

2.2. TOTAL LEAD CONTENT

Test method: With reference to CPSC-CH-E1003-09.1, analyzed by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES). [Reporting Limit: 10.0 mg/kg]

Test Item	Result [mg/kg]	Specification [mg/kg]
	Sample 003	
Total Lead content	< 10.0	≤ 90

Note:

- “mg/kg” denotes milligram per kilogram
- “<” denotes less than
- “≤” denotes not more than
- The specification is quoted from Consumer Product Safety Commission of U.S.A. Title 16, Code of Federal Regulation, part 1303 (CPSC 16 CFR 1303)

-----End of Report-----